

LIST OF UL-STYLES (single core cables)

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
1001	PVC/Nylon	300	80	0,23	30 – 16
1002	PVC	600	60	0,76	26 – 16
1003	PE, FRPE	300	60	0,76	26 – 16
1004	PVC/Nylon	–	80	0,20	30 – 16
1005	PVC/Nylon	–	90	0,20	26 – 16
1006	PVC/Nylon	–	105	0,20	26 – 16
1007	PVC	300	80	0,38	32 – 16
1011	PVC	600	80	0,76	28 – 9
1013	PVC	600	90	0,76	28 – 9
1015	PVC	600	105	0,76	28 – 9
1017	PVC	600	80	1,14	22 – 8
1019	PVC	600	80	1,52	8 – 2
1020	PVC	600	80	2,05	1 – 4/0
1022	PVC	600	80	2,78	–
1023	PVC	600	80	3,17	–
1024	PVC	600	90	1,14	18 – 8
1025	PVC/Nylon	600	90	1,14	8 – 6
1026	PVC	600	90	1,52	8 – 6
1027	PVC	600	90	1,91	1 – 4/0
1028	PVC	600	105	1,14	22 – 8
1029	PVC/Nylon	600	105	1,14	8 – 6
1030	PVC	1000	80	0,76	26 – 10
1031	PVC/Nylon	1000	80	0,76	26 – 10
1032	PVC	1000	90	0,76	26 – 10
1033	PVC/Nylon	1000	90	0,76	26 – 10
1037	PVC	300	60	0,30	24 – 20
1039	PVC	300	80	0,38	22 – 16
1040	P/B	300	80	–	22 – 16
1041	PVC	300	60	0,76	20 – 16
1043	PVC	300	80	0,76	20 – 16
1045	PVC	300	90	0,76	20 – 16
1049	PVC	300	80	1,14	20 – 16
1053	PVC	600	60	1,52	18 – 10
1054	PVC	600	80	1,52	18 – 10
1055	PVC	600	90	1,52	20 – 10
1056	PVC	600	105	1,52	20 – 10
1060	PVC	600	105	1,91	10 – 10
1061	SR PVC	300	80	0,23	30 – 16
1063	PVC	300	60	–	20 – 18
1095	PVC	300	80	0,30	30 – 16
1096	PVC/Nylon	300	80	–	26 – 10
1098	PE	2000	60	0,86	18
1099	PVC	300	80	0,38	28
1107	PE, FRPE	300	60	0,38	30 – 16
1108	PVC	300	80	–	26 – 16
1109	PVC, XPVC	300	90	0,38	26 – 16
1110	PVC; XPVC	300	105	0,38	26 – 16
1113	PE	600	60	–	26 – 16
1115	PVC	300/600	80	0,38	30 – 16
1116	PVC/Nylon	600	80	–	22 – 8
1118	PVC	300	90	0,38	26 – 16
1119	PVC	600	90	0,76	26 – 16
1120	PVC	600	105	0,76	30 – 4/0
1122	SR PVC	300	80	0,23	30
1123	PVC	300	80	0,76	22 – 20
1124	PVC	300	80	0,76	22 – 20
1158	PVC	300	60	0,76	22 – 9
1159	PVC	300	60	1,14	8
1160	PVC	300	60	0,38	22 – 16
1161	PVC	600	60	0,76	22 – 9
1162	PVC	600	60	1,14	22 – 9
1164	PTFE	300	150	0,33	32 – 10
1180	PTFE	300	200	0,38	28 – 10
1181	PVC/Nylon	600	60	0,76	18 – 16
1185	PVC	300	80	0,38	30 – 4/0
1195	PVC	300	80	0,38	26 – 14
1198	PTFE	600	150	0,51	26 – 10
1199	PTFE	600	200	0,51	26 – 10
1206	PVC	300	80	0,33	30 – 16
1208	PVC	300	80	0,33	26 – 16
1227	FEP	not specified*	105	0,20	32 – 14
1228	PVC	600	90	1,14	18 – 8
1229	PVC	600	90	1,52	8 – 2
1230	PVC	600	105	0,76	26 – 8
1231	PVC	600	105	1,14	18 – 8
1232	PVC	600	105	1,52/2,03	8 – 4/0
1233	PVC	600	80	1,52	18 – 8
1235	PVC	600	105	1,52	18 – 8
1237	PVC	600	80	1,14	22 – 19
1239	PVC	600	105	1,14	22 – 19
1270	PVC	600	90	1,14	18 – 9
1271	PVC	600	90	1,52	8 – 2
1272	PVC	600	90	1,91	1 – 4/0
1279	PVC	600	80	1,52	7 – 2
1280	PVC	600	80	1,14	18 – 8
1283	PVC	600	105	1,52	8 – 2
1284	PVC	600	105	1,91	1 – 4/0
1287	PVC	600	105	1,91	18 – 12
1306	PVC	600	80	2,29	8
1308	PVC	600	105	2,29	8

* not specified

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
1316	PVC/Nylon	600	105	0,38	26 – 12
1317	PVC/Nylon	600	105	0,51	10
1318	PVC/Nylon	600	105	0,76	8 – 6
1319	PVC/Nylon	600	105	1,02	4 – 2
1320	PVC/Nylon	600	105	1,27	1 – 4/10
1321	PVC/Nylon	600	105	1,78	250 – 1000
1322	PVC	600	90	1,91	14 – 10
1327	PVDF	–	105	0,25	30 – 16
1329	PVC	600	105	1,91	14 – 10
1330	FEP	600	200	variable	30 – 4/0
1331	FEP	600	105	variable	30 – 4/0
1332	FEP	300	200	0,38	30 – 10
1333	FEP	300	150	0,38	30 – 10
1335	PVC	600	90	0,76	22 – 10
1336	PVC	600	90	1,14	8
1337	PVC	600	90	1,52	6 – 2
1338	PVC	600	90	1,98	8 – 4/0
1366	PVC/PVC	600	90	variable	26 – 9
1394	PTFE	–	200	0,15	14 – 10
1400	PVC	600	90	1,14	14 – 10
1401	PVC	600	90	1,52	8
1402	PVC/Nylon	600	90	0,76	22 – 10
1405	PVC/Nylon	600	90	1,98	1 – 4/10
1408	PVC/Nylon	600	90	0,38	22 – 12
1409	PVC/Nylon	600	90	0,51	10
1410	PVC/Nylon	600	90	0,76	8 – 6
1411	PVC/Nylon	600	90	1,02	4 – 2
1412	PVC/Nylon	600	90	1,27	1 – 4/10
1413	PVC/Nylon	600	90	1,52	250 – 500
1414	PVC/Nylon	600	90	1,78	600 – 1000
1429	XPVC	150	80	0,25	32 – 16
1430	XPVC	300	105	0,38	30 – 16
1435	PE	300	80	0,41	26 – 16
1436	PE	300	80	0,79	26 – 16
1437	PE	300	80	1,63	26 – 16
1438	PE	300	80	1,14	26 – 16
1439	PE	300	80	0,81	26 – 16
1444	PVC	1000	90	1,14	18 – 10
1452	PVC/Nylon	1000	90	0,38	18 – 12
1453	PVC/Nylon	1000	90	0,51	10
1498	PCV	600	80	0,76	22 – 9
1499	PVC	600	90	0,76	22 – 9
1500	PVC	600	105	0,76	22 – 9
1508	ETFE	30	105	0,15	32 – 20
1517	ETFE	–	105	0,15	32 – 20
1523	ETFE	–	105	0,13	32 – 20
1533	PVC	–	80	0,23	30 – 10
1536	XPVC	–	80	0,25	30 – 10
1538	FEP	125	105	0,15	32 – 20
1542	PE-PVC	10000	80	–	24 – 10
1546	PE-PVC	600	–	–	20
1558	ETFE	–	125	0,10	32 – 20
1568	PVC	150	80	0,23	30 – 16
1569	PVC	300	105	0,38	28 – 10
1570	ETFE	600	250	–	24 – 8
1575	PVC	48	60	0,76	18 – 8
1581	PVC	300	80	0,38	14
1586	ETFE	–	105	0,20	32 – 6
1591	FEP	300	150	0,41	26 – 16
1592	FEP	300	200	0,41	26 – 16
1605	PVC	30	60	0,10	min. 46
1609	ETFE	125	105	0,13	32 – 6
1610	ETFE	not specified**	105	0,25	32 – 10
1612	PVDF	125	150	–	–
1618	PVC	300	80	0,38	–
1624	PVC	160	80	0,25	30 – 16
1662	PVC	300	80	variable	18 – 1/10
1680	PVC	–	105	–	18 – 1/10
1683	PVC	–	80	–	3/0
1692	PVC	30	80	2,54	min. 42
17107	PFA	30	200	0,127	32 – 20
1708	PFA	not specified**	200	0,127	32 – 20
1722	TPR	600	125	VAR	22 – 4/0
1729	PVC	300	80	0,22	32 – 16
1792	PE, PVC	30	80	0,05	min. 40
1847	FEP	30	105	0,08	min. 40
1848	FEP	300	150 o. 200	0,38	min. 24
1860	PFA	150	200	0,25	32 – 16
1888	TPR	300	125	0,41	–
1908	PVC	300	80	0,38	26 – 4/0
1909	PVC	600	80	0,76	26 – 4/0
1926	PE o. FRPE	300	60+80	0,17	30 – 16
1948	PVC	60	60	0,10	min. 46
1967	PVC	30	60+80	0,38	20 – 4/0
1968	PVC	–	60+80	0,38	20 – 4/0
1986	FEP	30	80	0,05	min. 50
1990	ETFE	600	105	0,50	30 – 4/0
1999	Zell. FEP	300	150	0,45	min. 36
10009	Zell. FEP	300	150	0,45	min. 36
10011	PFA	30	80	0,0254	min. 40
10030	PFA	300	250	0,025	30 – 10
10032	PFA	600	250	0,38	30 – 10
10050	FEP	600	150	0,457	30 – 4/0

LIST OF UL-STYLES (Multicore cables)

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
2006	PVC	300	80	1,14	20 - 16
2007	PVC	300	90	1,14	20 - 16
2012	PVC	300	80	1,52	18 - 16
2015	PVC	300	80	1,52	18 - 16
2030	PVC	600	80	1,91	14 - 10
2031	PVC	600	90	1,91	14 - 10
2032	PVC	600	105	1,91	14 - 10
2089	PVC	300	60	-	20 - 18
2090	PVC	300	60	-	20 - 18
2091	PVC	300	60	-	20 - 18
2092	PE	300	60	-	26 - 16
2093	PE	300	60	-	26 - 16
2094	PE	300	60	-	26 - 16
2095	PVC	300	90	-	32 - 16
2096	PVC	300	80	-	30 - 16
2097	PVC	300	80	-	30 - 18
2098	PVC	300	90	-	26 - 16
2099	PVC	300	90	-	26 - 16
2100	PVC	300	90	-	26 - 16
2101	PVC	300	105	0,38	30 - 16
2102	PVC	300	105	-	30 - 16
2103	PVC	300	105	0,38	30 - 16
2106	PE	600	60	-	26 - 12
2107	PE	600	60	-	26 - 12
2108	PE	600	60	-	26 - 12
2112	PVC	300	80	0,38	26 - 16
2113	PVC	300	80	0,38	26 - 16
2114	PVC	300	80	0,38	26 - 16
2115	PVC	600	80	-	26 - 16
2116	PVC	600	80	-	26 - 16
2117	PVC	600	80	-	26 - 16
2121	PVC	300/600	90	0,38	26 - 16
2122	PVC	300/600	90	0,38	26 - 16
2123	PVC	300/600	90	0,38	26 - 16
2124	PVC	600	90	0,76	28 - 9
2125	PVC	600	90	0,76	28 - 9
2126	PVC	600	90	0,76	28 - 9
2127	PVC	600	105	0,76	28 - 9
2128	PVC	600	105	0,76	29 - 9
2129	PVC	600	105	0,76	28 - 9
2243	PVC	300	105	1,14	20 - 16
2261	PVC	300	105	0,76	18
2262	PE	600 (isol.)	60	0,76	26 - 16
		300 (Jacket)			
2263	PE	600 (isol.)	60	0,76	26 - 16
		300 (Jacket)			
2264	PE	600 (isol.)	60	0,76	26 - 16
		300 (Jacket)			
2265	PVC	300	80	0,38	26 - 16
2266	PVC	300	80	-	26 - 16
2267	PVC	300	80	-	36 - 30
2268	PVC	300	80	-	26 - 16
2269	PVC	300	80	-	26 - 16
2270	PVC	300	80	-	26 - 16
2271	as for SVT	300	60	as for SVT	26 - 16
2272	as for SVT	300	60	as for SVT	26 - 16
2273	as for SVT	300	60	as for SVT	26 - 16
2274	as for SVT	300	60	as for SVT	26 - 16
2275	as for SVT	300	60	as for SVT	26 - 16
2276	as for SVT	300	60	as for SVT	26 - 16
2277	as for SVT	300	60	as for SVT	26 - 16
2278	as for SVT	300	60	as for SVT	26 - 16
2279	as for SVT	300	60	as for SVT	26 - 16
2280	as for SVT	300	60	as for SVT	26 - 16
2317	PE	600	60	-	26 - 16
2351	PE	600	80	-	26 - 16
2352	PE	300	80	-	26 - 16
2353	PE	300	80	-	26 - 16
2354	PE	600	80	-	26 - 16
2355	PE	600	80	-	26 - 16
2376	PVC	300	105	-	-
2384	variable	30	60	-	30
2385	VAR	30	60	-	30
2386	VAR	30	60	-	30
2387	VAR	30	60	-	30
2388	PVC	30	60	-	-
2405	PVC	300	80	-	30 - 16
2439	PE	600	80	-	26 - 16
2448	variable	30	60	-	30
2461	PVC	30	60	-	26 - 16
2462	PVC	300	60	-	-
2463	PVC	600	80	-	26 - 10

* not specified

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
2464	variable	300	80	-	-
2468	PVC	300	80	0,38	32 - 16
2474	PVC	600	105	-	26 - 16
2477	PVC	600	60	-	33 - 16
2483	PVC	600	105	-	26 - 16
2489	PVC	600	60	-	18
2490	AWM	not specified*	60	AWM	min. 36
2493	PP		60	-	30 - 16
2498	PE	300	80	-	28 - 16
2501	PVC	600	105	-	30
2502	variable	30	80	-	-
2504	PVC	600	105	-	20 - 14
2507	PVC	600	60	-	26 - 16
2516	PVC	600	105	-	30 - 9
2517	PVC	300	105	-	32 - 16
2532	PVC	30	60	-	30 - 16
2535	PVC	30	80	-	30 - 16
2548	PE	300	80	-	-
2549	PVC	300	90	-	30 - 16
2550	AWM	600	90	AWM	min. 40
2551	AWM	30	105	AWM	min. 40
2560	PVC	30	60	-	30
2564	PVC	125	75	-	22
2567	PVC	600	60	-	-
2570	PVC	600	80	-	30 - 9
2571	PVC	-	80	-	30 - 16
2574	AWM	30	105	AWM	min. 40
2576	PVC	150	80	-	30 - 9
2582	PE	150	60	-	30 - 16
2584	PVC	125	80	-	30 - 9
2586	PVC	600	105	-	30 - 9
2587	PVC	600	90	-	30 - 9
2589	AWM	30	105	AWM	see AWM Requirements
2598	VAR	300	60	-	30 - 16
2606	PE	300	60	-	30
2610	labeled Style 1007	300	80	labeled Style 1007	see 1007 Requirements
2614	AWM	30	105	AWM	min. 40
2623	PE	30	80	-	30 - 20
2626	AWM	30	80	AWM	not specified*
2629	PE	300	80	-	30 - 16
2630	AWM	125	90	AWM	30 - 9
2631	AWM	not specified*	90	AWM	min. 40
2637	AWM	30	90	AWM	min. 40
2653	AWM	600	90	AWM	36 - 6
2654	AWM	300	90	AWM	36 - 6
2655	PVC	300	80	-	33 - 10
2656	AWM	600	80	AWM	36 - 6
2660	AWM	not specified*	60	AWM	-
2661	AWM	300	105	AWM	36 - 6
2662	PVC	600	105	-	33 - 10
2668	AWM	30	60	AWM	min. 40
2678	PVC	30	105	-	-
2704	PVC	30	60	-	30
2778	AWM	150	60	AWM	30 - 16
2789	AWM	30	60	AWM	see AWM
2833	AWM	30	60	AWM	-
2835	PP	30	80	-	22
2919	PP	30	80	-	28 - 18
2920	AWM	30	60	AWM	min. 40
2921	AWM	30	60	AWM	min. 40
2930	AWM	not specified*	105	AWM	min. 40
2931	AWM	125	105	AWM	min. 40
2937	AWM	300	80	AWM	AWM
3071	S/GB	600	200	0,76	18 - 14
3075	S/GB	600	200	0,76	10 - 2
3173	XLPE	600	125	0,76	26 - 9
3199	XLPE	300	105	0,38	22 - 16
3212	SiR	600	150	1,14	26 - 10
3213	SiR	600	150	1,52	8 - 2
3214	SiR	600	150	1,91	1 - 4/0
3239	SiR	VAR	150	VAR	24 - 10
3265	XLPE	150	125	0,25	28 - 20
3266	XLPE	300	125	0,38	26 - 16
3271	XLPE	600	125	VAR	24 - 12
3272	XLPE	600	125	VAR	22 - 4
3291	XPVC	300	105	-	26 - 16
20063	PE	300	80	0,5	28 - 16
20083	PE	300	80	AWM	various AWG
20601	AWM	300	80	AWM	AWM